

## CLAIMS

What is claimed is:

- 5           1. A potentially elastic interlaced-textured yarn, comprising:  
          a potentially crimped yarn with a monofilament fineness of one to  
          six deniers and a total fineness of 20 to 300 deniers ; and  
          an ultrafine yarn with the monofilament fineness of 0.01 to 0.5  
          deniers and the total fineness of 30 to 300 deniers,  
10           whereby, one or two strands of the ultrafine yarn is interlaced  
          with plies the potentially crimped yarn.
2. The potentially elastic interlaced-textured yarn as set forth  
          in claim 1, wherein the potentially crimped yarn comprises a side-by-  
15           side type composite filaments having two kinds of polymers including  
          polyethylene terephthalate and polytrimethylene terephthalate.
3. The potentially elastic interlaced-textured yarn as set forth  
          in claim 1, wherein the ultrafine yarn is selected from the group  
20           consisting of a sea-island type composite filaments, a radial type  
          composite filaments and a very fine yarn produced through a direct  
          spinning process.
4. The potentially elastic interlaced-textured yarn as set forth  
25           in claim 1, wherein a potentially crimped yarn content is 11 to 67 wt%

based on a weight of the ultrafine yarn.

5. An elastic suede-like woven fabric with elongation of 10 to 40 % and elongation recovery of 80 % or more, comprising the potentially  
5 elastic interlaced-textured yarn as set forth in any one of claims 1 to 4.